

Kramer Industries, Inc.

140 Ethel Road West
Unit U
Piscataway, NJ 08854

phone: 888-515-9443
fax: 732-650-0556
www.KramerIndustriesOnline.com

“Right From The Start”

Aluminum Oxide Grit #1200 Mesh

Typical Physical Properties

Color	White
Grain Shape	Angular
Crystallinity	Coarse Crystal
Hardness	9 Mohs
Specific Gravity	3.8

Proximate Chemical Analysis

Al₂O₃	97.45 %	CaO	0.09 %
TiO₂	1.32 %	MgO	0.19 %
SiO₂	0.51 %	Na₂O	0.05 %
Fe₂O₃	0.33 %	K₂O	0.06 %

Particle Size Distribution

Size Distribution	Specification (microns) ¹		Result ²
	Lower Limit	Upper Limit	
Ds 3 ³	0.0	6.4	6.3
Ds 50 ⁴	2.6	3.6	3.5
Ds 94 ⁵	0.7	100.0	1.3

Notes:

FEPA-42.GB.1984 R-1993 (Sedigraph)

¹ Results obtained using Sedigraph settling test.

² Results of a recent batch.

³ DS 3 result indicates that 3% of distribution is the result and larger.

⁴ DS 50 result is median of particle size distribution.

⁵ DS 94 result indicates that 94% of distribution is the result and larger.