

Kramer Industries, Inc.

140 Ethel Road West
Unit U
Piscataway, NJ 08854

phone: 888-515-9443
fax: 732-650-0556
www.KramerIndustriesOnline.com

“Right From The Start”

Silicon Carbide Grit #22 Mesh

Typical Physical Properties

Color	Black
Grain Shape	Angular
Magnetic Content	0.2 – 0.5 %
Hardness	9.5 Mohs
Specific Gravity	3.2
Bulk Density	96 lbs / ft ³

Proximate Chemical Analysis

SiC	98.58 %	Fe	0.11 %
C	0.05 %	Al	0.02%
Si	0.80 %	CaO	0.03 %
SiO ₂	0.30 %	MgO	0.05 %

Particle Size Distribution

Screen Size	Size Grading Specification ¹		% Retention ²
	Lower Limit	Upper Limit	
14	0.0 %	0.0 %	0.0 %
18	0.0 %	20.0 %	15.8 %
25	70.0 %	100%	74.8 %
30	0.0 %	100%	8.1 %
-30	0.0 %	3.0 %	1.3 %
20 (CONTROL ³)	45.0 %	100 %	52.1 %

Notes:

Testing Method: FEPA Standards: 45-1986 and 42-1984

¹ Specification for percentage retained on each screen size for given grade of product.

² Results of a recent batch.

³ Control screen for quick confirmation of product grade.